

## Cabot's Cabothane Clear Oil Based Gloss

AUDW1642

|               |           |
|---------------|-----------|
| <b>Part A</b> | 864 82031 |
|---------------|-----------|

### Description

Cabot's Cabothane Clear Oil Based is a highly durable, hard wearing varnish suitable for use on timber doors, windows, trim and furniture. It is resistant to chemicals, oils, solvents and withstands abrasion, scuffing and scratching. It also contains UV absorbers, meaning it is Interior/Exterior durable and protects surfaces such as windows and doors that are exposed to sunlight. Cabot's Cabothane Clear also performs as a clear topcoat over Cabot's Interior Stain Oil Based.

### Features

- High durability.
- Resists stains & scratches.
- Enhances timber grain.
- Reduced odour & 6 hour recoat.
- UV resistant.

### Benefits

- Highly durable polyurethane coating to protect timber for longer.
- Cabothane is a tough coating that resists chemicals, abrasion, scuffing and scratching.
- Enhances the natural colour of the timber grain.
- Cabothane has reduced odour and can be recoated in just 6 hours.
- UV resistant to protect surfaces such as windows and doors which are exposed to sunlight.

### Uses

Timber doors, windows, trim and furniture.

### Precautions And Limitations

Do not apply this product in temperatures below 10°C or above 35°C, or when rain or heavy dew is expected during the drying period. If using outside in hot temperatures, do not apply in direct sunlight. Cool the timber by lightly dampening with water and coat in the shade.

Note: For surfaces subject to extreme UV exposure, use Cabot's Exterior Clear.

### Performance Guide

|                        |                                   |                 |                                   |
|------------------------|-----------------------------------|-----------------|-----------------------------------|
| <b>Weather</b>         | Interior and Exterior use.        | <b>Salt</b>     | Unaffected by splash or spillage. |
| <b>Heat Resistance</b> | Up to 100C.                       | <b>Water</b>    | Good.                             |
| <b>Solvent</b>         | Resists alcohol and hydrocarbons. | <b>Abrasion</b> | Moderate.                         |
| <b>Acid</b>            | Suitable for dilute splash.       | <b>Alkali</b>   | Suitable for dilute splash.       |

| Typical Properties                               |  |                        |                    |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
|--|--|------------------------|--------------------|-------------------------|----|--|--|--|------------|------------|--------------------|------------------------------------|--|--|----|------------------------------------|--|--|----|--------------------------|---------|--|--|--|--|--|----|
| <b>Gloss Level</b>                               | Gloss  | <b>Colour</b>          | Clear              |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Components</b>                                | 1  | <b>Number Of Coats</b> | 3                  |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Toxicity</b>                                  | Lead free  | <b>V.O.C. Level</b>    | < 455g/L           |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Touch Dry</b>                                 | 2 hours  |                        |                    |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Clean Up Description</b>                      | Mineral turpentine.<br>To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.  |                        |                    |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Application Method</b>                        |  <br>Air Spray      Brush  |                        |                    |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Application Conditions</b>                    | <table border="0" style="width: 100%;"> <tr> <td style="text-align: center;"><b>Solids By Volume</b></td> <td style="text-align: center;">43</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;"><b>Min</b></td> <td style="text-align: center;"><b>Max</b></td> <td style="text-align: center;"><b>Recommended</b></td> </tr> <tr> <td><b>Wet Film Per Coat (microns)</b></td> <td></td> <td></td> <td style="text-align: center;">63</td> </tr> <tr> <td><b>Dry Film Per Coat (microns)</b></td> <td></td> <td></td> <td style="text-align: center;">27</td> </tr> <tr> <td><b>Recoat Time (min)</b></td> <td style="text-align: center;">6 hours</td> <td></td> <td></td> </tr> <tr> <td><b>Theoretical Spread Rate (m<sup>2</sup>/L)</b></td> <td></td> <td></td> <td style="text-align: center;">16</td> </tr> </table> |                        |                    | <b>Solids By Volume</b> | 43 |  |  |  | <b>Min</b> | <b>Max</b> | <b>Recommended</b> | <b>Wet Film Per Coat (microns)</b> |  |  | 63 | <b>Dry Film Per Coat (microns)</b> |  |  | 27 | <b>Recoat Time (min)</b> | 6 hours |  |  | <b>Theoretical Spread Rate (m<sup>2</sup>/L)</b> |  |  | 16 |
| <b>Solids By Volume</b>                          | 43   |                        |                    |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
|  | <b>Min</b>   | <b>Max</b>             | <b>Recommended</b> |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Wet Film Per Coat (microns)</b>               |  |                        | 63                 |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Dry Film Per Coat (microns)</b>               |  |                        | 27                 |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Recoat Time (min)</b>                         | 6 hours  |                        |                    |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Theoretical Spread Rate (m<sup>2</sup>/L)</b> |  |                        | 16                 |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |
| <b>Typical Properties Notes</b>                  | SPREADING RATE<br>Approximately 16 square metres per litre depending on the porosity and condition of the timber.<br><br>DRYING AND RECOAT TIME<br>All timings quoted at 25C and 50% humidity. Cooler or humid conditions may require longer.  |                        |                    |                         |    |  |  |  |            |            |                    |                                    |  |  |    |                                    |  |  |    |                          |         |  |  |  |  |  |    |

| <b>Application Guide</b>                   |   |
|--|---|
| <b>Surface Preparation</b>                 | <ul style="list-style-type: none"> <li>▪ Note: Fill nail holes, cracks and other defects with Cabot's Wood Tone Putty after applying the first coat of this product for accurate colour matching.<br/>Remove stains, dirt, wax, grease and oil with mineral turpentine. Remove any polish with a suitable polish remover.</li> </ul> <p><b>BARE INTERIOR TIMBER</b><br/>Sand the surface smooth using 180 - 240 grit sandpaper. Sand only in the direction of the grain.<br/>Remove all traces of sanding dust.</p> <p><b>BARE EXTERIOR TIMBER</b><br/>Allow timber to weather for 4 - 6 weeks. For exterior surfaces only, clean with Cabot's Deck Clean following label instructions.</p> <p><b>PREVIOUSLY COATED INTERIOR TIMBER</b><br/>Thoroughly clean the surface with Cabot's Floor Clean and allow to dry. Sand with 180 - 240 grit sandpaper and remove all traces of sanding dust.<br/>Apply one coat to a small test area. Allow to dry for 6 hours. Press sticky tape firmly to the surface and pull off quickly. If the coating comes off, sand back to bare timber.<br/>If coating adheres well, sand the entire area with 180 - 240 grit paper for good adhesion, remove dust, then follow application instructions.</p> <p><b>PREVIOUSLY COATED EXTERIOR TIMBER</b><br/>For best results, remove back to bare timber using a paint stripper, or sanding. For exterior surfaces only, clean with Cabot's Deck Clean following label instructions.</p> |
| <b>Application Procedure And Equipment</b> | <ul style="list-style-type: none"> <li>▪ Note: Do not shake can.<br/>Stir thoroughly with a broad flat paddle before and during use.<br/>Apply with a good quality brush or spray gun. If spraying, back brushing is recommended. If brushing, always brush in the direction of the grain.<br/>Allow to dry for a minimum of 6 hours then lightly sand using 240 grit paper. Remove all sanding dust.<br/>Apply the 2nd &amp; 3rd coats as above, lightly sanding with 240 grit paper between each coat.</li> </ul> <p><b>STAINING BARE INTERIOR TIMBER</b><br/>If timber is to be stained, apply one coat of Cabot's Interior Stain Oil Based or Stain &amp; Varnish Oil Based following label instructions.<br/>For Cabot's Interior Stain Oil Based only: Allow stain to dry for 8 hours and apply 3 coats of Cabothane Clear following application procedure above.</p> <p>Note - To stain previously coated timber, sand back to bare timber before staining.</p> <p><b>HINTS</b><br/>Cabot's Cabothane Clear is not suitable for:<br/>previously wax coated finishes<br/>walk-on areas<br/>extreme UV exposure<br/>broad wall application</p> <p>For surfaces subject to extreme UV exposure, use Cabot's Exterior Clear.</p>   |

| Health And Safety   |   |                                 |  |
|---|---|---------------------------------|--|
| <b>MSDS Number</b>  | 13661263  | <b>Using Safety Precautions</b> | RISK: Flammable. Irritating to skin. Avoid contact with skin and eyes. Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying. If painting large areas wear an organic vapour respirator. This paint is flammable, so eliminate any sources of ignition. Do not smoke. |
| <b>Health Effects</b>                                     | <p>If poisoning occurs, contact a doctor or Poisons Information Centre AUST 131 126, NZ 0800 764 766.</p> <p>SWALLOWED: If swallowed, do NOT induce vomiting. Give a glass of water. Seek medical assistance.</p> <p>EYE: If in eyes, hold eyes open, flood with water for at least 15 minutes and see a doctor.</p> <p>SKIN: If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.</p> <p>For further information or a copy of the Product Safety Data Sheet telephone Cabots Customer Service Department on AUST 1800 011 006, NZ 0800 222 687.</p> <p>For emergencies phone AUST 1800 033 111, NZ 0800 734 607.</p> | <b>Flammability</b>             | This product is flammable.   |
| <b>Personal</b>   | Wear eye protection, protective clothing and gloves, and if spraying, wear a respirator with a combined vapour/particulate cartridge.   | <b>Storage</b>                  | Keep out of reach of children.   |
| <b>Disposal</b>   | Do not pour leftover paint down the drain. Unwanted paint should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collections. Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle the container via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may differ between local authorities. Check with your local council first.  |                                 |  |
| <b>In the case of emergency, please call 1800 033 111</b> |   |                                 |  |

| Transport And Storage        |                   |                      |                         |
|------------------------------|-------------------|----------------------|-------------------------|
| <b>Pack A</b>                | 864 82031         | <b>Shipment Name</b> | PAINTS                  |
| <b>Size</b>                  | 4L 1L 500ml 250ml | <b>Weight</b>        | 4.1Kg 1.1Kg 0.6Kg 0.3Kg |
| <b>Flash Point</b>           | >23C              | <b>UN Number</b>     | 1263                    |
| <b>Dangerous Goods Class</b> | 3                 | <b>Package Group</b> | III                     |

**Disclaimer**

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427