

Feast Watson Floor Paint Satin

AU_DW01799

Part A	710-line
---------------	----------

Description
Feast Watson FLOOR PAINT is an opaque, water based coating for interior timber floors. FLOOR PAINT has been specially formulated to provide superior mar resistance and deliver outstanding adhesion and wear resistance for longer lasting results. FLOOR PAINT can be used on new and existing interior timber, cork and parquet floors. It is ideal for interior timber flooring subject to high wear, and can be tinted to a wide range of colours.





Features
<ul style="list-style-type: none"> • Mar and wear resistant • Extremely long lasting • Water based • Tintable to many colours

Benefits
<ul style="list-style-type: none"> • Low odour, fast drying and easy water clean up • No clear top coat required

Uses
On new and existing interior timber, cork and parquet floors.

Precautions And Limitations
Do NOT apply this product at temperatures below 10°C or above 35°C.

Performance Guide			
Weather	Interior only	Salt	N/A
Heat Resistance	Softens at temperatures above 70C	Water	Good water resistance, unaffected by splash or spillage
Solvent	Sensitive to aromatic hydrocarbons, alcohols and ketones	Abrasion	Good Resistance to Abrasion
Acid	N/A	Alkali	N/A

Typical Properties																											
Gloss Level	Satin	Thinner	Water.																								
Colour	2 bases tintable to many colours	Components	1																								
Number Of Coats	2 - 3	Toxicity	Lead free. Dry film is non-toxic																								
V.O.C. Level	<65g/L untinted	Meets GBCA VOC Requirement?	Yes. Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.																								
Touch Dry	30 Minutes																										
Clean Up	 Water																										
Clean Up Description	Clean all equipment with water																										
Application Method	   Brush Roller Pad																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">28</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td></td> <td style="text-align: center;">75</td> <td style="text-align: center;">89</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td></td> <td style="text-align: center;">21</td> <td style="text-align: center;">25</td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">2 hours</td> <td></td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td></td> <td style="text-align: center;">12</td> <td style="text-align: center;">10</td> </tr> </table>			Solids By Volume	28				Min	Max	Recommended	Wet Film Per Coat (microns)		75	89	Dry Film Per Coat (microns)		21	25	Recoat Time (min)	2 hours			Theoretical Spread Rate (m²/L)		12	10
Solids By Volume	28																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)		75	89																								
Dry Film Per Coat (microns)		21	25																								
Recoat Time (min)	2 hours																										
Theoretical Spread Rate (m²/L)		12	10																								
Typical Properties Notes	COVERAGE • Softwood: 8 - 10m ² per litre. • Hardwood: 10 - 12m ² per litre. • Cork 8 - 10m ² per litre. Drying times are given at 25°C and 50% relative humidity. Lower temperatures and higher humidity can lead to extended drying times. Allow 24 hours before light foot traffic and 72 hours for normal traffic. Full curing after 7 days.																										

Application Guide

Surface Preparation	<ul style="list-style-type: none"> • New or Bare Timber/Cork • Punch exposed nails below the surface. Holes and imperfections should be filled with timber putty. • Sand timber to an even, smooth surface. Vacuum and wipe to remove dust. • Prepare uncoated cork tiles in accordance with the supplier's recommendation. <p>Previously Coated Timber</p> <ul style="list-style-type: none"> • Clean surface with Feast Watson FLOORCLEAN and allow to dry. • Sand surface thoroughly until a uniform matt appearance is achieved. • Vacuum and wipe to remove dust. • Check adhesion by applying FLOOR PAINT to a small test area. Allow to dry for 24hrs then firmly press a strip of sticky tape over the test area and rip off quickly. If coating is removed, it will not adhere to the surface so the surface needs to be sanded back to bare timber. If coating is not removed, sand the test area back to a uniform matt surface. • If previous coating has worn back to expose bare timber it must be completely removed.
Application Procedure And Equipment	<ul style="list-style-type: none"> • Surfaces to be coated must be dry and free from all dirt, dust, grease, wax, polish and oil. • FLOOR PAINT should be mixed thoroughly, with a flat blade stirrer, before and during application, taking care NOT to introduce bubbles. • Apply with a Feast Watson FLOOR FINISH APPLICATOR, brush or short nap mohair roller. Work along the whole length of 3 - 4 floorboards at a time, maintaining a wet edge to prevent lap marks and lay off in the direction of the grain. Take care to not introduce bubbles. • When the first coat is thoroughly dry, apply second coat as outlined above. Note, if grain raising is present a light sand is required before the second coat. • For a longer wearing finish apply a third coat as per previous instruction. • If a gloss finish is applied, apply a suitable gloss water based floor coating, such as Cabot's CFP or Intergrain ULTRAFLOOR, as per label instructions. • Do NOT apply this product at temperatures below 10°C or above 35°C. <p>MAINTENANCE</p> <ul style="list-style-type: none"> • Regularly clean using FLOORCLEAN. • Monitor the surface for signs of colour loss or surface defects. When floor requires an additional coat of FLOOR PAINT, apply as per the instructions for Previously Coated Surfaces. <p>THINNING</p> <ul style="list-style-type: none"> • In hot temperatures thin with up to 100mls of water per litre to ease application and slow drying.

Health And Safety

MSDS Number	22934	Using Safety Precautions	Keep out of reach of children. Avoid contact with skin and eyes. Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying.
Health Effects	<p>SWALLOWED: If swallowed, do NOT induce vomiting. Give a glass of water. Seek medical assistance.</p> <p>EYE: Rinse with plenty of running water. Seek medical help if irritation occurs.</p> <p>SKIN: If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.</p>	Flammability	This product is non-flammable.
Storage	Keep out of reach of children.	Disposal	Do not pour leftover paint down the drain. Unwanted paint should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collections. Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle the container via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may differ between local authorities. Check with your local council first.

In the case of emergency, please call 1800 033 111

Transport And Storage

Pack A	Floor Paint	Shipment Name	Not dangerous Goods. No special transport requirements
Size	4L	Weight	5 kg
Flash Point	N/A	UN Number	N/A
Dangerous Goods Class	N/A	Package Group	N/A

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427