

Feast Watson Black Japan Floor Finish Satin

AU_DW01801

Part A	710 W0002
---------------	-----------

Description
Feast Watson BLACK JAPAN FLOOR FINISH is an oil based interior floor finish which combines a traditional Black Japan stain with a professional clear polyurethane for one-step 'Black Japan look' and durable protection. The semi-transparent coating adds rich colour whilst allowing the grain pattern of timber to remain visible.





Features
<ul style="list-style-type: none"> Traditional Black Japan stain combined with a professional clear polyurethane Retains timber grain

Benefits
<ul style="list-style-type: none"> No clear top coat required Multiple coats build colour and depth

Uses
All interior timber flooring

Precautions And Limitations
This is a three coat flooring system. If the desired colour is achieved in less than three coats, complete the system with Feast Watson FLOORCLEAR as per label instructions. Do NOT apply this product at temperatures below 10°C or above 35°C.

Performance Guide			
Weather	Interior Use Only	Heat Resistance	Softens at temperatures above 70C
Water	Good water resistance, unaffected by splash or spillage	Solvent	Sensitive to aromatic hydrocarbons, alcohols and ketones
Abrasion	Good Resistance to Abrasion	Alkali	N/A

Typical Properties																											
Gloss Level	Satin	Components	1																								
Number Of Coats	1+	Toxicity	Lead free																								
V.O.C. Level	<495 g/l	Touch Dry	8 Hours																								
Clean Up	 Thinner																										
Clean Up Description	Mineral turpentine. To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.																										
Application Method	   Brush Roller Pad																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">41</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">12 hours</td> <td></td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td></td> <td style="text-align: center;">12</td> <td></td> </tr> </table>			Solids By Volume	41				Min	Max	Recommended	Wet Film Per Coat (microns)				Dry Film Per Coat (microns)				Recoat Time (min)	12 hours			Theoretical Spread Rate (m²/L)		12	
Solids By Volume	41																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)																											
Dry Film Per Coat (microns)																											
Recoat Time (min)	12 hours																										
Theoretical Spread Rate (m²/L)		12																									
Typical Properties Notes	<p>DRYING TIME Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times. Touch Dry: 8 hours. Recoat: 12 hours. Allow 24 hours before light foot traffic and 72 hours for normal traffic. Full curing after 7 days.</p> <p>COVERAGE Softwood: 8 - 10m² per litre. Hardwood: 10 - 12m² per litre. Cork: 8 - 10m² per litre.</p>																										

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> ▪ NEW OR BARE TIMBER/CORK Punch exposed nails below the surface. Holes and imperfections should be filled with timber putty. Sand timber to an even, smooth surface. Vacuum and wipe to remove dust. Prepare uncoated cork tiles in accordance with the supplier's recommendation. PREVIOUSLY COATED TIMBER Previously coated surfaces need to be sanded back to bare timber. Remove all sanding dust before coating.
Application Procedure And Equipment	<ul style="list-style-type: none"> ▪ Stir BLACK JAPAN FLOOR FINISH thoroughly before and during use with a flat blade stirrer, being careful not to introduce bubbles. If using more than one can of the same colour to complete a job, combine both cans and stir thoroughly. Test colour on an off-cut or inconspicuous area prior to coating the whole job to ensure satisfaction with colour choice. Apply with a Feast Watson FLOOR FINISH APPLICATOR, brush or short nap mohair roller. Work along the whole length of 3 - 4 floorboards at a time, maintaining a wet edge to prevent lap marks and lay off in the direction of the grain. Take care to not introduce bubbles. This is a three coat flooring system. If the desired colour is achieved in less than three coats, complete the system with Feast Watson FLOORCLEAR as per label instructions. Stronger colour can be developed with further coats of BLACK JAPAN FLOOR FINISH. Continue applying coats by the above procedure, sanding between coats, until the desired colour is achieved. <p>MAINTENANCE Regularly clean using Feast Watson FLOORCLEAN. Monitor the surface for signs of colour loss or surface defects. When floor requires an additional coat of BLACK JAPAN FLOOR FINISH, apply as per the instructions for Previously Coated Surfaces.</p> <p>THINNING In hot temperatures thin with up to 100mls of mineral turpentine per litre to ease application and slow drying.</p>

Health And Safety			
MSDS Number	22936	Using Safety Precautions	Keep out of reach of children. Avoid contact with skin and eyes. Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying. If painting large areas wear an organic vapour respirator. This paint is flammable, so eliminate any sources of ignition. Do NOT smoke.
Health Effects	FIRST AID: For advice contact a Doctor or Poisons Information Centre on AUST 13 11 26, NZ 0800 764 766. SWALLOWED: If swallowed, do NOT induce vomiting. Give a glass of water. Seek medical assistance. EYE: Rinse with plenty of running water. Seek medical help if irritation occurs. SKIN: If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.	Flammability	This product is flammable.
Storage	Keep out of reach of children.	Disposal	Do not pour leftover paint down the drain. Unwanted paint should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collections. Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle the container via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may differ between local authorities. Check with your local council first.
In the case of emergency, please call 1800 033 111			

Transport And Storage			
Pack A	Black Japan Floor Finish	Shipment Name	DANGEROUS GOODS
Size	4L	Weight	3.89
Flash Point	> 23 C	UN Number	1263
Dangerous Goods Class	3	Package Group	III

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427