

Feast Watson Timber & Deck Stain

AU_DW01894

Part A	863-line
---------------	----------

Description

Feast Watson TIMBER & DECK STAIN is a penetrating, semi-transparent exterior timber finish. TIMBER & DECK STAIN adds rich colour and a subtle sheen to timber, highlighting the natural of the timber grain. The two coat system is ideal for transforming the colour of timber, or rejuvenating the colour of old, weathered timber. With its oil rich formula, TIMBER & DECK STAIN protects timber from the destructive effects of water, UV and mould. TIMBER & DECK STAIN is resistant to cracking, peeling and blistering and is suitable for use over bare and previously coated timber that is prepared as per the below instructions. TIMBER & DECK STAIN can also be used for inside/outside colour matching. It is ideal for doors, interior exposed beams, window frames and skirting boards. For a satin or gloss finish on vertical surfaces TIMBER & DECK STAIN can be overcoated with Feast Watson CLEAR VARNISH (Interior) or WEATHERPROOF™ VARNISH (Exterior).

Note: CLEAR VARNISH and WEATHERPROOF VARNISH are NOT suitable for coating areas subject to foot traffic.

Features

- Penetrating, semi-transparent exterior timber finish.
- Long lasting.

Benefits

- Adds rich colour and a subtle sheen to timber, highlighting the natural beauty of the timber grain.
- Protects timber from the destructive effects of water, UV and mould.

Uses





Suitable for use over bare and previously coated timber that is prepared as per the below instructions. TIMBER & DECK STAIN can also be used for inside/outside colour matching. It is ideal for doors, interior exposed beams, window frames and skirting boards.

Precautions And Limitations

Do not apply in temperatures under 10°C or above 35°C or when rain or heavy dew is expected within the coating dry time.

Performance Guide

Weather	Exterior durable.	Salt	Good.
Water	Very good.	Solvent	Suitable for splash.
Abrasion	Good.	Acid	Suitable for splash.
Alkali	Suitable for splash.		

Typical Properties																											
Gloss Level	Low Sheen	Colour	4 packaged colours.																								
Number Of Coats	2	V.O.C. Level	< 580g/L																								
Meets GBCA VOC Requirement?	No	Touch Dry	6 hours																								
Clean Up Description	Mineral turpentine To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.																										
Application Method	 Air Spray  Airless Spray  Brush  Pad																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">29</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">12 hours</td> <td></td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td></td> <td style="text-align: center;">12</td> <td></td> </tr> </table>			Solids By Volume	29				Min	Max	Recommended	Wet Film Per Coat (microns)				Dry Film Per Coat (microns)				Recoat Time (min)	12 hours			Theoretical Spread Rate (m²/L)		12	
Solids By Volume	29																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)																											
Dry Film Per Coat (microns)																											
Recoat Time (min)	12 hours																										
Theoretical Spread Rate (m²/L)		12																									
Typical Properties Notes	<p>DRYING TIME Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times. Touch Dry: 6 hours Recoat: 12 hours Walk on 24 hours</p> <p>COVERAGE Softwood: 8-10m² per litre Hardwood: 10-12m² per litre</p>																										

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> EXTERIOR TIMBER PREPARATION NEW TIMBER Allow new timber to weather in its final position for 4 - 6 weeks. Prepare timber for coating with Feast Watson WOODCLEAN™ as per the instructions. For best results, lightly sand the surface to remove any grain raise. Remove all sanding dust before coating. WEATHERED TIMBER Prepare weathered or grey timber by cleaning thoroughly with WOODCLEAN as per the instructions. Sanding may be required to remove stains and restore deteriorated surfaces. Remove all sanding dust before coating. PREVIOUSLY COATED TIMBER Previously coated surfaces need to be taken back to bare timber by stripping or sanding. Prepare timber for coating with WOODCLEAN as per the instructions.
Application Procedure And Equipment	<ul style="list-style-type: none"> Allow the timber to dry completely before applying TIMBER & DECK STAIN. TIMBER & DECK STAIN should be stirred thoroughly before and during application a flat blade stirrer taking care not to introduce bubbles. If the job requires more than one can of stain, mix all together in one large container prior to commencing. Apply two coats of TIMBER & DECK STAIN using a brush, spray or Feast Watson Floor Applicator. If applying with spray, back brush the coating to ensure even penetration. Work along 3 - 4 planks at a time, in the direction of the grain. Ensure edges and end grain are fully coated. Allow 12 hours drying between coats. <p>Note: One coat is normally sufficient for interior timber. A second coat would only be required to achieve greater depth of colour and greater protection. For a satin, or gloss finish on vertical surfaces overcoat with CLEAR VARNISH (Interior) or WEATHERPROOF VARNISH (Exterior) as per label instructions.</p> <p>Note: CLEAR VARNISH and WEATHERPROOF VARNISH are NOT suitable for coating areas subject to foot traffic.</p> <p>MAINTENANCE Regularly monitor coated timber for signs of colour loss, dryness and weathering. If required, clean the surface using WOODCLEAN, allow the surface to dry and recoat with one coat of TIMBER & DECK STAIN. Note that additional coats will result in developing a stronger colour.</p>

Health And Safety			
MSDS Number	23575	Using Safety Precautions	Avoid contact with skin and eyes. Provide adequate ventilation. This paint is flammable, so eliminate any sources of ignition. Do NOT smoke.
Health Effects	<p>RISK: Flammable. Irritating to skin. May cause sensitisation by skin contact. Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.</p> <p>FIRST AID: For advice, contact a Poisons Information Centre (Phone Australia 13 11 26; New Zealand 0800 764 766) or a doctor.</p> <p>SWALLOWED: If swallowed, do NOT induce vomiting. Give a glass of water. Seek medical assistance.</p> <p>EYE: Rinse with plenty of running water. Seek medical help if irritation occurs.</p> <p>SKIN: If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.</p>	Flammability	This product is flammable.
Storage	Keep out of reach of children.	Disposal	Do NOT pour leftover product down the drain. Keep unwanted product in sealed containers for disposal via special chemical waste collections. Disposal of empty containers via domestic kerbside recycling programs may differ between local authorities. Check with your local council first.

In the case of emergency, please call 1800 033 111

Transport And Storage			
Pack A	863-line	Shipment Name	PAINTS
Size	4L 2L 250ml	Weight	4.02kg 2.07kg 0.30kg
Flash Point	>23C	UN Number	1263
Dangerous Goods Class	3	Package Group	III

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427