

Teknos AQUATOP 2600 Satin

AU_DW01991

Part A	720-W0152, W0153, W0154, W0155
---------------	--------------------------------

Description
Teknos AQUATOP 2600 is a water based finish coat for use with the Teknos fully factory applied system. Available in opaque and translucent shades, it produces a subtle satin sheen. Suitable for interior and exterior use. Must be applied by spray to ensure a high quality finish.



Features
<ul style="list-style-type: none"> • Designed for spray application • Available in opaque and translucent shades • Water based

Benefits
<ul style="list-style-type: none"> • Produces a high quality finish • Wide colour range • Low odour, easy clean up and quick drying

Uses
Use as the topcoat for the Teknos fully factory applied system. Suitable systems are available for a wide range of timbers. AQUATOP 2600 must be applied by spray application to achieve a high quality finish.

Precautions And Limitations
This product is designed for spray application only. In order to achieve UV-protection with translucent colours, the film thickness must be at least 80um dry (approx. 225um wet).

Performance Guide	
Weather	For interior and exterior use.

Typical Properties																							
Gloss Level	Satin	Colour	Tintable to opaque and translucent shades																				
Number Of Coats	1-2	V.O.C. Level	30-60g/L depending on colour																				
Touch Dry	2-3hrs																						
Clean Up	 Water																						
Application Method	 Airless Spray																						
Application Conditions	Solids By Volume 37 <table border="0"> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td style="text-align: center;">150</td> <td style="text-align: center;">300</td> <td></td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">2</td> <td></td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td style="text-align: center;">3</td> <td style="text-align: center;">6</td> <td></td> </tr> </table>		Min	Max	Recommended	Wet Film Per Coat (microns)	150	300		Dry Film Per Coat (microns)				Recoat Time (min)	2			Theoretical Spread Rate (m²/L)	3	6			
	Min	Max	Recommended																				
Wet Film Per Coat (microns)	150	300																					
Dry Film Per Coat (microns)																							
Recoat Time (min)	2																						
Theoretical Spread Rate (m²/L)	3	6																					
Typical Properties Notes	Drying times are determined at 20C and 50% relative humidity. Drying times may vary according to wood quality, temperature, humidity, ventilation and film thickness.																						

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> • MAINTENANCE Conduct a routine 12 monthly maintenance inspection. Best protection of the timber and ease of maintenance is ensured if AQUATOP 2600 is recoated before deterioration of the coating and timber underneath occurs. First indication of the need for recoating will be observed as patchiness or discolouration on edges and areas where insufficient product has been applied. To apply a maintenance coat to a surface which is in good condition, clean the surface with Reviva and apply one coat of Cabots Exterior Varnish Stain or Intergrain Natural Stain in a suitable colour • The timber must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13% and should not exceed 15%. All Class 3 or 4 timber, and Accoya, must be treated with AQUAPRIMER 2907-02.
Application Procedure And Equipment	<ul style="list-style-type: none"> • This product is supplied ready for use. Stir well before use. <p>Recommended spray settings: Nozzle - Airless flat 0.28 mm, Pressure - 100-110 bar</p>

Health And Safety	
MSDS Number	DLXFGREN000172
In the case of emergency, please call 1800 033 111	

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427