

Feast Watson Black Japan Floor Finish Satin on New Timber Flooring [Interior]

AU_SW11248

Description
<p>Feast Watson BLACK JAPAN FLOOR FINISH is an oil based interior floor finish which combines a traditional Black Japan stain with a professional clear polyurethane for one-step 'Black Japan look' and durable protection. The semi-transparent coating adds rich colour whilst allowing the grain pattern of timber to remain visible.</p> <p>Feast Watson SANDING SEALER levels rough surfaces to create flawless, mirror finish coatings. SANDING SEALER is a clear and quickly dries to a hard film which fills open grain and marked timbers. SANDING SEALER can be dry sanded to create a super smooth finish with no grain pattern. Top-coat SANDING SEALER with Feast Watson CLEAR VARNISH, WEATHERPROOF VARNISH or STAIN & VARNISH. It is also a perfect preparation to remove grain texture from timber prior to French polishing or painting.</p>

Substrate And Substrate Preparation	
Substrate Notes:	<p>New, uncoated timber.</p> <p>Comments: Tannin Rich Timber Tannins are water-soluble extractives present in some timbers such as meranti, merbau, kwila, western red cedar and tallowwood. These tannins are leached out by water or moisture and can cause staining of surrounding areas. They are seen as dark coloured stains either under or within a coating.</p> <p>Naturally oily timber Some timbers such as cypress, spotted gum, tallowwood, brush box, teak and yellow balau are naturally oily. These oils can slow down the drying of a coating. Old uncoated timber, which may be grey and weathered, and/or have dry rot, mould, fungus, grain cracking, staining, dirt or other surface contamination. PREVIOUSLY OILED OR STAINED EXTERIOR TIMBER Exterior timber that had been previously coated with either a penetrating oil or stain.</p> <p>Not to be used on previously painted timber. Timber that has been previously coated with either a penetrating oil or stain, or with a film forming coating such as a clear varnish or paint.</p>
Substrate Preparation Notes:	<p>Punch all nail heads approx. 3 mm below surface of timber. Fill nail holes, cracks and other defects with a wood filler and allow to dry thoroughly. Do not use linseed oil putty. Sand in the direction of the grain and along the full length of the boards. Depending on the roughness of the timber, progress through the grades of sandpaper, finishing with a final sand using no finer than 240 grit. Remove all sanding dust.</p>

Coating System Summary	
Primer:	AUDW0744: Feast Watson Sanding Sealer
1st Coat:	AU_DW01801: Feast Watson Black Japan Floor Finish Satin
2nd Coat:	AU_DW01801: Feast Watson Black Japan Floor Finish Satin
Optional:	AU_DW01801: Feast Watson Black Japan Floor Finish Satin
Please refer to the coating system details below	

Coating System			
Coat Type:	Primer	Datasheet:	AUDW0744 Feast Watson Sanding Sealer
Application Methods:	   Air Spray Brush Roller		
	Theoretical Spread Rate *	Min	Max
	Wet Film Per Coat (microns)		10
	Dry Film Per Coat (microns)		100
	Recoat Time **	6 hours	Indefinite
Coating Application Details:	Apply SANDING SEALER using a brush, roller or spray gun. If applying by spray, add 20% of mineral turpentine to thin product. Allow to dry before sanding off all surface material with medium grade sand paper. Apply 1-2 coats of SANDING SEALER depending on grain depth. Two or more coats may be required when applying by spray. Thoroughly remove all dust from the surface prior to applying finish coats. STAINING Apply Feast Watson PROOFTINT stain after the final SANDING SEALER coat has been sanded, and prior to the application of top coats. Top Coats Finish by coating the surface with CLEAR VARNISH, WEATHERPROOF VARNISH or STAIN & VARNISH following the label instructions.		
Coat Type:	1st Coat	Datasheet:	AU_DW01801 Feast Watson Black Japan Floor Finish Satin
Application Methods:	   Brush Roller Pad		
	Theoretical Spread Rate *	Min	Max
	Recoat Time **	12 hours	12
Coating Application Details:	Stir BLACK JAPAN FLOOR FINISH thoroughly before and during use with a flat blade stirrer, being careful not to introduce bubbles. If using more than one can of the same colour to complete a job, combine both cans and stir thoroughly. Test colour on an off-cut or inconspicuous area prior to coating the whole job to ensure satisfaction with colour choice. Apply with a Feast Watson FLOOR FINISH APPLICATOR, brush or short nap mohair roller. Work along the whole length of 3 - 4 floorboards at a time, maintaining a wet edge to prevent lap marks and lay off in the direction of the grain. Take care to not introduce bubbles. This is a three coat flooring system. If the desired colour is achieved in less than three coats, complete the system with Feast Watson FLOORCLEAR as per label instructions. Stronger colour can be developed with further coats of BLACK JAPAN FLOOR FINISH. Continue applying coats by the above procedure, sanding between coats, until the desired colour is achieved. MAINTENANCE Regularly clean using Feast Watson FLOORCLEAN. Monitor the surface for signs of colour loss or surface defects. When floor requires an additional coat of BLACK JAPAN FLOOR FINISH, apply as per the instructions for Previously Coated Surfaces. THINNING In hot temperatures thin with up to 100mls of mineral turpentine per litre to ease application and slow drying.		

Coat Type:	2nd Coat	Datasheet:	AU_DW01801 Feast Watson Black Japan Floor Finish Satin
Application Methods:	   Brush Roller Pad		
Theoretical Spread Rate *		Min	Max
Recoat Time **		12 hours	12
Recommended			
Coating Application Details:	<p>Stir BLACK JAPAN FLOOR FINISH thoroughly before and during use with a flat blade stirrer, being careful not to introduce bubbles. If using more than one can of the same colour to complete a job, combine both cans and stir thoroughly.</p> <p>Test colour on an off-cut or inconspicuous area prior to coating the whole job to ensure satisfaction with colour choice.</p> <p>Apply with a Feast Watson FLOOR FINISH APPLICATOR, brush or short nap mohair roller. Work along the whole length of 3 - 4 floorboards at a time, maintaining a wet edge to prevent lap marks and lay off in the direction of the grain. Take care to not introduce bubbles.</p> <p>This is a three coat flooring system. If the desired colour is achieved in less than three coats, complete the system with Feast Watson FLOORCLEAR as per label instructions.</p> <p>Stronger colour can be developed with further coats of BLACK JAPAN FLOOR FINISH.</p> <p>Continue applying coats by the above procedure, sanding between coats, until the desired colour is achieved.</p> <p>MAINTENANCE Regularly clean using Feast Watson FLOORCLEAN. Monitor the surface for signs of colour loss or surface defects. When floor requires an additional coat of BLACK JAPAN FLOOR FINISH, apply as per the instructions for Previously Coated Surfaces.</p> <p>THINNING In hot temperatures thin with up to 100mls of mineral turpentine per litre to ease application and slow drying.</p>		
Coat Type:	Optional	Datasheet:	AU_DW01801 Feast Watson Black Japan Floor Finish Satin
Application Methods:	   Brush Roller Pad		
Theoretical Spread Rate *		Min	Max
Recoat Time **		12 hours	12
Recommended			
Coating Application Details:	<p>Stir BLACK JAPAN FLOOR FINISH thoroughly before and during use with a flat blade stirrer, being careful not to introduce bubbles. If using more than one can of the same colour to complete a job, combine both cans and stir thoroughly.</p> <p>Test colour on an off-cut or inconspicuous area prior to coating the whole job to ensure satisfaction with colour choice.</p> <p>Apply with a Feast Watson FLOOR FINISH APPLICATOR, brush or short nap mohair roller. Work along the whole length of 3 - 4 floorboards at a time, maintaining a wet edge to prevent lap marks and lay off in the direction of the grain. Take care to not introduce bubbles.</p> <p>This is a three coat flooring system. If the desired colour is achieved in less than three coats, complete the system with Feast Watson FLOORCLEAR as per label instructions.</p> <p>Stronger colour can be developed with further coats of BLACK JAPAN FLOOR FINISH.</p> <p>Continue applying coats by the above procedure, sanding between coats, until the desired colour is achieved.</p> <p>MAINTENANCE Regularly clean using Feast Watson FLOORCLEAN. Monitor the surface for signs of colour loss or surface defects. When floor requires an additional coat of BLACK JAPAN FLOOR FINISH, apply as per the instructions for Previously Coated Surfaces.</p> <p>THINNING In hot temperatures thin with up to 100mls of mineral turpentine per litre to ease application and slow drying.</p>		
Coating System Notes:	<p>* Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application and surface roughness.</p> <p>** Recoat times are quotes for 25°C and 50% relative humidity, these may vary under different conditions.</p>		

Comments
<ul style="list-style-type: none"> Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point. Do not apply if the surface temperature is greater than 40°C or below 10°C, or likely to fall below 10°C during the application or drying period. Do not apply paint if the temperature is below 10°C or likely to fall below 10°C during the drying period. This is an abridged specification and must be read in conjunction with the FULL Dulux specification and product data sheet(s).

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427