

AUIN00670 Intergrain Endure 1 Pack Matt, Satin and Gloss

Introduction

Line Shade

Matt 701W0610

Satin 701W0609

Gloss 701W0608

Description and Image

Intergrain Endure 1 Pack is a clear water based one pack polyurethane for interior timber flooring, stairs, parquetry and cork. It can also be used on prefinished flooring. Available in Matt, Satin and Gloss.

Green building compliant

The Green Building Council of Australia (GBCA) target for VOC level of high performance floor coatings is <140 g/L.

Endure 1 Pack can be used on Green Star Buildings as it emits less VOCs than the target set by the GBCA.

Slip resistance

A slip resistant finish can be achieved by adding Intergrain UltraGrip at a level of 5% to Intergrain Endure 1 Pack. When tested according to AS4586:2013, the following slip ratings are achieved:

- Endure 1 Pack with UltraGrip in 1 coat = P4
- Endure 1 Pack with UltraGrip in 2 coats = P5

See application guide section for system details.



Features and Benefits

- Ideal for residential use
- Long lasting
- Non-yellowing
- Easy application
- Formulated and tested for Australian conditions

Uses

Interior timber flooring, stairs, parquetry and cork.
Can also be used on prefinished flooring.

Precautions and Limitations

Do not apply in temperatures above 35°C or below 10°C.

If using in temperatures above 30°C, Intergrain Wet Edge Extender can be added to Intergrain Endure 1 Pack to a maximum of 5%, to ease application. Follow instructions on the Intergrain Wet Edge Extender label.

Performance Guide			
Weather Interior only			
Water Good for splashes and spillage		Abrasion Good	

Typical Properties																							
Gloss Level Matt <20%, Satin 30-40%, Gloss >80%	Heat Thinner Intergrain Wet Edge Extender																						
Colour Clear																							
Components 1	Number of Coats 2 minimum																						
V.O.C. Level <75g/L																							
Meets GBCA V.O.C. Requirements? Yes Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.																							
Touch Dry 2 hours																							
Clean Up  Water																							
Clean Up Description Clean equipment and tools with water																							
Application Methods  Brush  Roller																							
Application Conditions <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th>Min</th> <th>Max</th> <th>Recommended</th> </tr> </thead> <tbody> <tr> <td>Wet Film Per Coat (microns)</td> <td> </td> <td> </td> <td>100</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td> </td> <td> </td> <td>28</td> </tr> <tr> <td>Recoat Time (min/hours)</td> <td>4 hours</td> <td> </td> <td> </td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td> </td> <td> </td> <td>10</td> </tr> </tbody> </table>					Min	Max	Recommended	Wet Film Per Coat (microns)			100	Dry Film Per Coat (microns)			28	Recoat Time (min/hours)	4 hours			Theoretical Spread Rate (m ² /L)			10
	Min	Max	Recommended																				
Wet Film Per Coat (microns)			100																				
Dry Film Per Coat (microns)			28																				
Recoat Time (min/hours)	4 hours																						
Theoretical Spread Rate (m ² /L)			10																				
Typical Property Notes Solids Matt = 28% Satin = 28% Gloss = 28% Coverage																							

8 – 10m²/L depending on the porosity of the timber.

Dry times

Dry times are based on drying conditions of 25°C and 50% relative humidity. Drying times will be longer in conditions cooler than 25°C or more humid than 50% humidity.

Touch Dry: 2 hours.

Re-coat: Allow a minimum of 4 hours drying between coats.

Floors will take light foot traffic after 12 hours, and normal foot traffic after 3 days.

Full cure: Allow 7 days.

Replace furniture after 7 days.

Application Guide

Surface Preparation

All surfaces must be clean, dry, free of wax, grease, dust and other contaminants. The presence of contaminants increases the possibility of rejection and delamination.

Clean oily timbers such as Brushbox, Spotted Gum, Cypress and Tallowwood with methylated spirits and allow to dry.

Prepare cork in accordance with cork manufacturer's instructions.

All nail holes and cracks should be filled with water based putty. Do not use linseed oil putty.

Ensure floor is even; sand to a flat even surface if required. Final sand should be with 150 mesh screenback, and vacuum thoroughly with a commercial grade vacuum cleaner to remove all sanding dust.

Application Procedure and Equipment

Mixing

Shake Intergrain Endure 1 Pack for at least 1 minute to ensure any settled matting agent is reincorporated.

Strain product before use.

Application

It is recommended to shield doorways, fireplaces and windows from dust, dirt or other contaminants settling on the surface between coats, as this will affect the finished appearance. Do not completely seal, as adequate ventilation is required to assist with drying.

Do not apply in temperatures above 35°C or below 10°C.

If using in temperatures above 30°C, Intergrain Wet Edge Extender can be added to Intergrain Endure 1 Pack to a maximum of 5%, to ease application, follow instructions on the Intergrain Wet Edge Extender label.

New timber

Apply 1 coat of Intergrain Timberseal™ Water Based, Intergrain Timberseal Alcohol Based or Intergrain Timberseal Ultra following the instructions on the label. Lightly sand Intergrain Timberseal Ultra with a worn 180 mesh screen if needed. If using Intergrain Timberseal Water Based or Intergrain Timberseal Alcohol Based, DO NOT SAND.

Apply 2 coats of Intergrain Endure® 1 Pack. Cut in edges using a brush, then apply to the rest of surface using a 10mm nap microfibre roller.

Finishing strokes should be in the direction of the grain. To improve adhesion and minimise grain raise, it is recommended to screen between coats with a worn 150 grit screen or 180 grit screen.

To increase the wear resistance, apply 3 coats of Intergrain Endure 1 Pack. On porous timbers, apply 3 coats of Intergrain Endure 1 Pack to ensure a uniform finish.

Previously finished surfaces: including Floating Floors

Wash the floor with Intergrain Floor Cleaner as per the label instructions. Sand to a dull finish with a 100 grit screen, vacuum thoroughly to remove dust, then wipe clean with a damp rag.

To ensure adhesion, a test patch is recommended after the surface has been prepared. Apply a small test area with Intergrain Endure 1 Pack, allow to dry for 24 hours then firmly press a strip of sticky tape over the coating and rip off quickly. If the coating is removed, sand the full surface back to bare timber. If the coating is not removed, sand the test area back to a dull finish. Apply 1–2 coats of Intergrain Endure 1 Pack using a 10mm nap microfibre roller. To improve adhesion, it is recommended to screen between coats with a worn 150 grit screen or 180 grit screen.

If patches of the previous coating have worn back to expose bare timber, the full floor must be sanded back to bare timber, and product applied as per 'new timber' directions.

Slip resistance

Intergrain UltraGrip™ can be added to Endure 1 Pack to achieve a more slip resistant finish. It is not recommended to add Intergrain UltraGrip to Endure 1 Pack Gloss as it will dull the gloss finish.

To achieve a wet slip resistance rating of P4

- 1 coat Enviropro Timberseal.
- 1 coat Enviropro Endure 1 Pack, with 5% Intergrain UltraGrip added.
- 1 coat Enviropro Endure 1 Pack.

To achieve a wet slip resistance rating of P5

- 1 coat Enviropro Timberseal.
- 2 coats Enviropro Endure 1 Pack, with 5% Intergrain UltraGrip added to each coat.

Intergrain UltraGrip must be added at a rate of 5%. That is 250g of UltraGrip for 5L of coating
When UltraGrip is added, the sheen or gloss level of the resultant coating will be lower than normal.
When using UltraGrip, do not sand the coat that contains the UltraGrip.
When using UltraGrip with Endure 1 Pack, decant the Endure product into another clean container before adding the UltraGrip. While stirring, add UltraGrip slowly to avoid generating dust. Stir in UltraGrip thoroughly with a flat blade stirrer or drill mixer until fully mixed in and lump-free. Stir regularly during use.

Health and Safety

SDS Number
DLXGHSEN005089

SDS Link

Using Safety Precautions
Refer to SDS

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A
Intergrain Endure 1 Pack

Size:

Weight:

Matt 5L Satin 5L Gloss 5L

Matt 5.31kg Satin 5.29kg Gloss 5.27

Please refer to the Safety Data Sheet for full safety, health and transportation information.

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.