



Specification CPWB0073	26.03.2019
-------------------------------	-------------------

Enviropro Hard Wax Oil on interior timber
--

Substrate
New or uncoated interior timber.

Coating System Summary	
Surface Preparation	Sand
1 st coat	Enviropro Hard Wax Oil
2 nd coat	Enviropro Hard Wax Oil



Specification CPWB0073	26.03.2019
-------------------------------	-------------------

Coating Details	
Surface Preparation	Sand
Application Details	Sand following industry best practice. Remove all sanding dust.
Precautions and Limitations	Wear appropriate personal protective equipment.

1st coat	Enviropro Hard Wax Oil
Application Method	Brush, Roller, Cloth
Spreading Rate	20-24m ² /L The first coat may require more depending on the porosity and age of the timber.
Recoat Time	Touch Dry: 2 hours. Recoat: 4 hours. Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times.
Application Details	Hard Wax Oil does NOT require thinning. Surfaces to be coated must be dry and free from all dirt, dust, grease or polish. Hard Wax Oil should be stirred thoroughly before and during application with a flat blade stirrer taking care not to introduce bubbles. Apply a coat of Hard Wax Oil to the timber with a brush, roller or cloth. Ensure the surface is evenly covered. Once first coat is thoroughly dry, any grain raise can be removed by lightly sanding with 240 grit sandpaper, being careful not to sand through the coating. When the first coat is thoroughly dry, apply a second coat of Hard Wax Oil following the application process outlined above.
Wash Up	Clean all application equipment with mineral turpentine. To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place used cloths on top of each other.
Precautions and Limitations	Do not apply in temperatures below 10°C or above 35°C



Specification CPWB0073	26.03.2019
-------------------------------	-------------------

2nd coat	Enviropro Hard Wax Oil
Application Method	Brush, Roller, Cloth
Spreading Rate	20-24m ² /L The first coat may require more depending on the porosity and age of the timber.
Recoat Time	Touch Dry: 2 hours. Recoat: 4 hours. Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times.
Application Details	Hard Wax Oil does NOT require thinning. Hard Wax Oil should be stirred thoroughly before and during application with a flat blade stirrer taking care not to introduce bubbles. Apply a coat of Hard Wax Oil to the timber with a brush, roller or cloth. Ensure the surface is evenly covered. For floors allow 24 hours before light foot traffic and 72 hours for normal traffic. Full curing after 7 days. Replace furniture after 7 days.
Wash Up	Clean all application equipment with mineral turpentine. To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place used cloths on top of each other.
Precautions and Limitations	Do not apply in temperatures below 10°C or above 35°C

This specification is to be read in conjunction with the following Product Data Sheets	
---	--

Enviropro Hard Wax Oil	AUDW02533
------------------------	-----------

Please refer to the datasheet for full information.



Specification CPWB0073	26.03.2019
-------------------------------	-------------------

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427